



DATASHEET

Stand: 01. JANUARY 2023

	TENSILE	FLEXURAL
MODULUS [GPA]	27,2	30,9
STRENGTH [MPA]	243	322
ELONGATION [%]	1,5	2,0

NOTE: MECHANICAL TESTS HAVE BEEN CARRIED OUT ON THE BASIS OF SPECIMINES WITH 50 % FUSE UD TAPES AND 50% THERMOSET RESINS

FACTS BEHIND FUSE: 100% BIOBASED, EFFICIENT PROCESSING, HIGHLY FLEXIBLE IN AREA WEIGHT BETWEEN 80 AND 250 g/m²